

DAYGLO

DAYCHROME - MIDDLE CHROME DM-13

Full Tone

Reduction 1:10

DAYCHROME Middle Chrome DM-13 is a general purpose Middle Chrome used in the manufacture of Synthetic Enamels and Printing Inks. This pigment is stabilized and offers good fastness to light and weather.

TECHNICAL DATA

Colour Index No.	77603	RESISTANCE TO LIGHT	
Colour Index Pigment No.	Y-34	Full Tone	7
Oil Absorption	15-20	Tint Tone (1:10)	6
Specific Gravity	5.1-6.0	RESISTANCE TO	
Bulk Density g/cc	0.87	Acid	G
		Alkali	P
BLEEDING IN		APPLICATIONS	
Water	5	Paints	*
5% Caustic Soda	3	Printing Inks	*
5% Hydrochloric Acid	3	Rubber	
Linseed Oil	5	Leather Pastes	*
Ethanol	5	Linoleum	*
Ethyl Acetate	5	PVC Leather Cloth	*
Xylene	5	Paper Coating	*
n-Butanol	5	Chalk / Crayons	
Methyl Ethyl Ketone	5	Plastics	*
Mineral Turpentine	5		
Cellosolve	5		
Diocetyl Phthalate	5		
RESISTANCE TO HEAT			
120 C / 30 min.	SB		
150 C / 20 min.	SB		
180 C / 10 min.	SB		
210 C / 10 min.	USB		

LEGEND

COLOUR	BLEEDING	HEAT STABILITY	LIGHTFASTNESS	APPLICATIONS	E - EXCELLENT
Y - YELLOW	SCALE (1-5)	SB : STABLE	SCALE (1-8)	* - RECOMMENDED	VG - VERY GOOD
R - RED	5:NO BLEED	USB : UNSTABLE	1 - POOR	/MAYBE USED	G - GOOD
W - WHITE	1:CONSIDERABLE BLEED		8 - EXCELLENT		F - FAIR P - POOR