

DAYGLO

DAYCHROME - MIDDLE CHROME DM-14

Full Tone

Reduction 1:10

This Pigment is highly stabilized, and is a pre-darkened Chrome, providing excellent light fastness and exterior durability. Therefore, this pigment is most suitable for high quality coatings meant for Auto refinishing purposes. It possesses good resistance to acidic environment. Therefore this pigment is strongly recommended for Paints where better Light Fastness is required.

TECHNICAL DATA

Colour Index No.	77603	RESISTANCE TO LIGHT	
Colour Index Pigment No.	Y-34	Full Tone	8
Oil Absorption	15-20	Tint Tone (1:10)	8
Specific Gravity	5.1-6.0	RESISTANCE TO	
Bulk Density g/cc	0.62	Acid	G
		Alkali	P
BLEEDING IN		APPLICATIONS	
Water	5	Paints	*
5% Caustic Soda	3	Printing Inks	*
5% Hydrochloric Acid	3	Rubber	
Linseed Oil	5	Leather Pastes	*
Ethanol	5	Linoleum	*
Ethyl Acetate	5	PVC Leather Cloth	*
Xylene	5	Paper Coating	*
n-Butanol	5	Chalk / Crayons	
Methyl Ethyl Ketone	5	Plastics	*
Mineral Turpentine	5		
Cellosolve	5		
Diocetyl Phthalate	5		
RESISTANCE TO HEAT			
120 C / 30 min.	SB		
150 C / 20 min.	SB		
180 C / 10 min.	USB		
210 C / 10 min.	USB		

LEGEND

COLOUR	BLEEDING	HEAT STABILITY	LIGHTFASTNESS	APPLICATIONS	E - EXCELLENT
Y - YELLOW	SCALE (1-5)	SB : STABLE	SCALE (1-8)	* - RECOMMENDED	VG - VERY GOOD
R - RED	5:NO BLEED	USB : UNSTABLE	1 - POOR	/MAYBE USED	G - GOOD
W - WHITE	1:CONSIDERABLE BLEED		8 - EXCELLENT		F - FAIR
					P - POOR